

Using Microorganisms for Cleaning Oil-Contaminated Concrete

Issayeva A.U.¹ Babenko A.S.² Sattarova A.M.¹ Tleukeeva A.Ye.¹ Issayev Ye.B.^{1*}
 1.M.Auezov South Kazakhstan State University, Shymkent, 160012, Tauke khan avenue, 5, Kazakhstan
 2.Tomsk State University, Lenin avenue, 36, Tomsk, 634050 Russia
 * E-mail of the corresponding author: akissayeva@mail.ru

Abstract

Revealed that the distribution of spots on the surface of the concrete depends on its density and structure, and the penetration of oil into the concrete occurs through micro- and nano-pores and cracks of the further spread of spots along the pathways. It was found that the use of hydrocarbon-oxidizing microorganisms strains as *Micrococcus luteus* IS16, *M. varians* IS41, micromycetes: *Aspergillus* sp., *Penicillium* sp., *Alternaria* sp., thiobacteria *Acidithiobacillus ferrooxidans* Ach1, *A. ferrooxidans* Ach2 promising for biological treatment of oil-contaminated concrete. Create optimal conditions for maintaining the activity of microorganisms: $55,0 \pm 15,0\%$ moisture, nutrients, temperature $38,0 \pm 2,0^{\circ}\text{C}$, trace elements, optimize the biodegradation of petroleum hydrocarbons.

Keywords: oil-contaminated concrete, bioremediation, hydrocarbon-oxidizing microorganisms, thiobacteria.

1. Introduction

The problem of environmental pollution by oil and oil products takes, recently, one of the leaders in the environment. There are studies conducted in different countries and associated with biological treatment of soil and water from oil and oil products using a variety of biological objects (Admon *et al.* 2001, Hutchinson *et al.* 2004, Ainon *et al.* 2006, Nejada *et al.* 2011). Particular attention is given to hydrocarbon-oxidizing microorganisms (HOM) as the main consumer of petroleum hydrocarbons (Chaineau *et al.* 2003, 2005, Azlinah *et al.* 2008, Obuekwe *et al.* 2008, Milic *et al.* 2009, Obayori *et al.* 2009). However, information on the biological treatment of oil-contaminated surfaces concreted scarce (Beklemishev & Kozliak 2003, Kogbara 2014), mostly using different detergents. Most likely, this is due to the porosity of concrete and asphalt, which complicates the process of deep cleaning of the substrate from organic pollutants.

The purpose of work- study the possibility of biological treatment of oil-contaminated concrete using microorganisms based on a study of the migration of oil.

2. Material and methods of researches

Collection of Samples: Samples of concrete were selected in test laboratory of construction materials. As material of research blocks of various brands of concrete of $10,0 \pm 0,5 \times 10,0 \pm 0,5$ cm in size served.

Oil. In researches oil of the Kumkol field with the following characteristics was used: temperature of hardening 100°C , contents silikagel of pitches of 19,2%; karbeno-karboides of 5,82%; asfalten of 5,4%; paraffin of 7,5%; sulfurs of 0,064%. At a temperature of 200°C has density – 0,850 g/cm³.

Physic-Chemical Properties of Contaminated Concrete: The concrete physic-chemical parameters were analyzed. The temperature was determined using a mercury thermometer. Nature of penetration and distribution of an oil slick in concrete blocks was investigated visually and with the helpelectronic and raster microscope "Jeol JSM-6490 LV" (Japan).

Isolation and Enumeration of Bacteria: Isolation and enumeration of bacteria were performed by soil dilution plate technique using mineral salts agar media. One gram of dried soil was dissolved in 9ml of distilled water and agitated vigorously. Different aqueous dilutions, 10, 10, 10 of the suspension were applied on to plates and 20ml of melted medium at around 50°C was added to it. After gently rotating, the plates were incubated at 37°C for 24 hours. Enumeration of different isolates was carried out. Selected colonies of bacteria were transferred from mixed culture of the plates on to respective agar plates and incubated at 37°C for 24 hours. Plates containing pure cultures were stored at 4°C until for the examinations.

Isolation and screening cultures. HOM: a. Mineral salts medium (MSM) (g/L): K_2HPO_4 (2g), KH_2PO_4 (0.5g), NaCl (0.5g), NH_4Cl (0.5g), MgSO_4 (0.2g), CaCl_2 (10mg), pH 7.2, containing different concentration of diesel and kumkol oil. b. Enrichment medium (EM): meat extract, peptone culture medium and glucose medium. c. Preservation medium (PM): meat extract, peptone, agar medium (MPA).

Micromycetes: The fungi were extracted by direct print method and dry needle method (Methods of experimental mycology, 1982). The cultures were grown using humid camera method and on the Czapek culture media. Samples were incubated in Petri dishes at a temperature of 25°C . Starting on the 7th day, the dishes were examined and micromycetes colonies were isolated into pure culture. Incubation period lasted for 21 days. Upon pure cultures isolation, Czapek agar was used for their identification and further storage.

Thiobacteria: For the growth of bacterial strains, iron Liquid medium (9kFe2+) (by Sugio *et al.* 2008).

Characterization of Isolates: Each isolate was examined many times for its size, shape, margin, consistency opacity, elevation, pigmentation, Gram reaction and cell morphology as described by Holt et al (1994). Diagnostic properties used include motility, production of catalase, indole, urease, oxidative fermentation of sugars, methyl red test, vogues proskauer test and citrate utilization test.

3. Results of researches

After putting oil on a surface of concrete blocks features of their distribution in horizontal and vertical vectors were studied (**Figure 1**).

Besides, for studying of possibility of cleaning of concrete blocks of oil them the microanalysis for definition of element and weight structure was carried out previously (**Table 1**).

It was revealed that the smallest depth of penetration of oil in samples 1, 2 and 8, but diameter of an oil slick on a block surface the greatest.. Electronic and microscopic inspection showed that the structure of these blocks dense without jointing, as explains spreading of a spot on a block surface. In blocks 3, 5, 6 and 9 oil gets deep into micro and nanocracks. In blocks 2, 4, 7 and 10 oil there passes through micropores. Thus it is visible that oil drops located in ways of penetration, pollute to 10-12% of nearby concrete (**Figure 2**). It is visible by this fact and difficulties in cleaning of a surface of the petropolluted concrete speak.

For cleaning of the petropolluted concrete blocks as options synthetic detergents in the form of powder and gel, HOM composition consisting of strains of *Micrococcus luteus* IS16, *M. varians* IS41 with a caption of 10^8 C/ml, composition of thiobacteria (Tb) of *Acidithiobacillus ferrooxidans* Ach1, *A. ferrooxidans* Ach2, composition of micromycetes which were applied in 1,0 ml on a surface of an oil slick were used. It was established that use as HOM, micromycetes and thiobacteria is more effective than chemical means (**Figure 3**).

Thus it was revealed that creation of optimum conditions for maintenance of activity of microorganisms somehow: $55,0 \pm 15,0\%$ humidity, biogenous elements, temperature $38,0 \pm 2,0^\circ\text{C}$ (**Figure 4**), optimize processes of biodegradation of hydrocarbons of oil.

4. Conclusion

On the basis of the conducted researches it is established that nature of oil pollution of concrete depends on their structure. Penetration of oil in concrete happens by means of micro and a nanotime and cracks to further distribution of a spot along ways of penetration. Most likely, difficulties in purification of the petropolluted concrete and asphalt are also connected with it. Oil slicks remain even after carrying out actions for physical and chemical cleaning that is confirmed by visual inspections of the petropolluted concreted sites at a number of the enterprises of oil and gas branch. Besides, the used cleaners promote secondary environmental pollution. Results of these researches show prospects of use of compositions of microorganisms which biodegradations of hydrocarbons of oil promote. Creating favorable conditions for their activity: $55,0 \pm 15,0\%$ humidity, biogenous elements, temperature $38,0 \pm 2,0^\circ\text{C}$, microcells, optimize processes optimizes processes of biological purification of the petropolluted concrete.

References

- Admon, S., Green, M., Avnimelech, Y., 2001. Biodegradation Kinetics of Hydrocarbons in Soil during Land Treatment of Oily Sludge. *Bioremediation Journal* 5(3), 193-209.
- Ainon, H., Mohamad, Nik Mohd, N., Wan Yusoff, W.M., 2006. Petroleum hydrocarbon degrading bacteria from oil contaminated site: isolation, screening, identification and degradation studies. *Proceeding 8th National Biological Symposium*, 1-6.
- Azlinah, M. S., Lee, K. C., Aishah, H., Chee, M. S., Darah, I., Ibrahim, C. O. 2008. Isolation, screening and identification of potential petroleum hydrocarbon degraders. *Proceedings of the 6th Regional IMTGT-UNINET Conference*, 146-149.
- Beklemishev M.K., Kozliak E.I. Bioremediation of Concrete Contaminated with n-Hexadecane and Naphtalene. *Acta Biotechnol.*, 2003, vol. 23, pp. 197-210.
- Chaineau, C.H., Yepremian, C., Vidalie, J.F., Ducreux, J., Ballerini, D., 2003. Bioremediation of Crude Polluted Soil: Biodegradation, Leaching and Toxicity Assessment. *Water, Air and Soil Pollution* 144, 419-440.
- Chaineau, C.H., Rougeux, G., Yepremian, C., Oudot, J., 2005. Effects of Nutrient Concentration on the Biodegradation of Crude Oil and Associated Microbial Populations in the Soil. *Soil Biology & Biochemistry* 37, 1490-1497.
- Holt, J.G., N.R. Krieg, P.H.A. Sneath, J.T. Staley and S.T. Williams, 1994. *Bergey's Manual of Determinative Bacteriology*. 9th Ed. Williams and Wilkins.m pp: 71-561.
- Kobraga R.B. 2014. Encouraging microbial activity in cementitious systems: an emerging frontier in contaminated soil treatment. *Journal of Chemical Technology & Biotechnology*, Volume 88, Issue 4, pp 501-507.
- Methods of experimental mycology / Ed. V.I. Bilay. Kiev. 1982. 346 p. (in Russian)
- Milic J. S., Beskoski V. P., Ilic M. V, Ali S. A. M., Gojgic-Cvijovic G. D. and Vrvic M. M. Bioremediation of

soil heavily contaminated with crude oil and its products: composition of the microbial consortium. Journal of the Serbian Chemical Society, vol.74, Jul. 2009, pp. 455-460, doi: 10. 2298/JSC0904455M 455.

Nejada V. 2011. Application of biostimulante in benzo(a)pyrene polluted soils: Short-time effects on soil biochemical properties./ Benitez, C., Parrado, J. // Apple Soil Ecol. 2011.-50.- P.-21-26.

Obayori, O.S., Adebuseye, S.A., Adewale, A.O., Oyetibo, G.O., Oluyemi, O.O., Amokun, R.A., Ilori, M.O. 2009. Differential degradation of crude oil (Bonny Light) by four Pseudomonas strains. Journal of Environmental Sciences 21, 243-248.

Obuekwe C.O., Al-Jadi Z. K. and Al-Saleh E.S., Al-Saleh Esmaeil S. Hydrocarbon degradation in relation to cell-surface hydrophobicity among bacterial hydrocarbon degraders from petroleum-contaminated Kuwait desert environment," International Biodeterioration & Biodegradation, Vol. 63, Apr. 2009, pp. 273–279, doi: 10. 1016/j. ibiod. 2008. 10. 004.

Sugio T, Wakabayashi M, Kanao T, Takeuchi F (2008) Isolation and Characterization of Acidithiobacillus ferrooxidans Strain D3-2 Active in Copper Bioleaching from a Copper Mine in Chile. *Biosci. Biotechnol. Biochem.* 72(4): 998–1004.

Akmaral U.Issayeva, ScD, Professor of Biology, Director of the Institute of Ecology and Biotechnology. PhD thesis "A role of spontaneous microflora in sewage treatment of concentrating factories from cyanic connections" (1994), ScD thesis "Microbiology and biotechnology of cleaning of the petropolluted soils and waters in the conditions of arid climate of the South Kazakhstan" (2006). Area of scientific interests - ecological biotechnology. The author of a number of ways of bioremediation of the petropolluted soils in the conditions of arid climate of South Kazakhstan, biological purification of industrial sewage, biological deactivation of pyrophoric sulfides of iron, phytoremediation of toxic waste. Has a number of the state awards, including the diploma "The best inventor of the Republic of Kazakhstan for 2001-2005", breastplates "For a contribution to development of domestic science".

Andrey S. Babenko, ScD, Professor of Ecology, Tomsk State University PhD thesis "Rove beetles (Coleoptera, Staphylinidae) of the south part of West Siberia" (1983), ScD thesis "Ecology of Staphylinidae of forest and disturbed territories of South Siberia" (1999). Sphere of scientific interests include ecology of soil invertebrates, organic waste decomposition. The main awards: Fulbright Scholarship (2001-2002), Rockefeller Foundation (2003), Green Found Grant (2010).

Aigul M. Sattarova, doctoral PHD. Fields of research - the study of the processes of bioremediation of oil-contaminated substrates.

Asel Ye.Tleukeeva, Master of Biology, Research Associate. Fields of research - the study of the reaction of microorganisms on a variety of factors.

Yerzhan B.Issayev, PhD, associate professor, has been studying the effect of xenobiotics on biological objects. PhD thesis "Flora of Southern Altai" (1994).




Figure 1. Nature of distribution of oil in concrete blocks

Table 1. Element and weight structure of concrete blocks

Blocks	Na	Mg	Al	Si	S	Cl	K	Ca	Fe
1	0.97±0.80	3.03±0.29	5.07±0.48	7.74±0.65	1.96±0.15	0.42±0.02	1.13±0.09	38.54±3.25	5.39±0.50
2	5.96±0.48	*	0.60±0.05	2.17±0.18	17.51±1.52	*	33.35±2.87	4.70±0.41	3.51±0.21
3	*	0.59±0.04	0.63±0.05	3.88±0.35	0.60±0.03	*	0.52±0.04	22.76±2.14	*
4	1.17±0.11	2.26±0.19	2.17±0.20	8.58±0.64	2.18±0.20	*	1.02±0.01	44.68±4.42	2.62±0.11
5	*	0.19±0.01	1.61±0.15	7.69±0.59	*	*	*	5.39±0.45	*
6	0.28±0.02	2.26±0.21	2.17±0.19	8.58±0.72	1.53±0.11	*	1.02±0.01	44.68±4.23	2.62±0.18
7	1.09±0.10	2.55±0.23	2.32±0.20	9.05±0.82	2.39±0.18	1.12±0.10	0.25±0.01	42.61±3.92	3.05±0.21
8	*	0.38±0.02	0.41±0.03	2.05±0.15	*	*	*	10.37±1.01	*
9	2.40±0.19	*	2.51±0.19	0.34±0.02	2.35±0.18	1.36±0.10	9.54±0.81	7.46±0.52	2.59±0.19
10	2.40±0.21	*	2.78±0.21	0.34±0.03	2.39±0.19	1.36±0.09	9.57±0.85	8.1±0.74	3.01±0.24

Note: * - it isn't revealed




Figure 2. Electronic and raster pictures of cuts of the petropolluted blocks 2 (a) ,6 (b) and 7(c)(h1000)




Figure 3. Extent of cleaning of concrete blocks of oil with detergents: gel and powder, microorganisms: HOM- hydrocarbon-oxidizing microorganisms, micromycetes, Tb- thiobacteria




Figure 4. Influence of temperature on process of bioremediation of the petropolluted concrete

The IISTE is a pioneer in the Open-Access hosting service and academic event management. The aim of the firm is Accelerating Global Knowledge Sharing.

More information about the firm can be found on the homepage:

<http://www.iiste.org>

CALL FOR JOURNAL PAPERS

There are more than 30 peer-reviewed academic journals hosted under the hosting platform.

Prospective authors of journals can find the submission instruction on the following page: <http://www.iiste.org/journals/> All the journals articles are available online to the readers all over the world without financial, legal, or technical barriers other than those inseparable from gaining access to the internet itself. Paper version of the journals is also available upon request of readers and authors.

MORE RESOURCES

Book publication information: <http://www.iiste.org/book/>

Academic conference: <http://www.iiste.org/conference/upcoming-conferences-call-for-paper/>

IISTE Knowledge Sharing Partners

EBSCO, Index Copernicus, Ulrich's Periodicals Directory, JournalTOCS, PKP Open Archives Harvester, Bielefeld Academic Search Engine, Elektronische Zeitschriftenbibliothek EZB, Open J-Gate, OCLC WorldCat, Universe Digital Library, NewJour, Google Scholar

